

Product Technical Datasheet – Polyethylene wax

Edition Date: 20.11.2020

Edition Number: 1

Grade: VTR-112 (PR)

Specifications

Parameter	Test method	Unit	Value
Appearance	-	-	prills
Melting point	ASTM 3418	[°C]	112-120
Density	ASTM 1505	[g/cm ³]	0.93-0.95
Viscosity	ASTM D3236	[cp]	30±10
Penetration	ASTM 1321	[dmm]	2-5
Packaging	-	Kg	20

For more information, please visit our website: <http://www.vektanchemical.com>

DISCLAIMER: Although all statements and information contained herein are believed to be accurate and reliable, they are presented without guarantee or warranty of any kind, express or implied. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liability for use of the information and results obtained. Statements or suggestions concerning the use of materials and processes are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all toxicity data and safety measures are indicated herein or that other measures may not be required.

November 2020, Tashkent, Uzbekistan
© 2020 VT Chemical
All rights reserved